The University of Bradford Institutional Repository

<http://bradscholars.brad.ac.uk>

This work is made available online in accordance with publisher policies. Please refer to the repository record for this item and our Policy Document available from the repository home page for further information.

To see the final version of this work please visit the publisher's website. Access to the published online version may require a subscription.

Link to publisher version: <http://dx.doi.org/10.1016/j.istruc.2016.12.001>

Citation: Mashiri FR, Mirza O and Lam D (2017) Post-fire Behaviour of Innovative Shear Connection for Steel-Concrete Composite Structures. Structures. 9: 147-156.

Copyright statement: © 2017 Elsevier. Reproduced in accordance with the publisher's self-archiving policy. This manuscript version is made available under the [CC-BY-NC-ND 4.0 license](#).

POST FIRE BEHAVIOUR OF INNOVATIVE SHEAR CONNECTION FOR COMPOSITE STEEL-CONCRETE STRUCTURES

Fidelis R. Mashiri^a, Olivia Mirza^a, Carlo Canuto^a & Dennis Lam^b

^a School of Computing, Engineering and Mathematics, Locked Bag 1797, Penrith 2175, New South Wales, Australia

^b School of Engineering, University of Bradford, Bradford, West Yorkshire, BD7 1DP, UK

ABSTRACT:

Steel-concrete composite structures are commonly used in buildings and bridges because it takes advantage of tensile strength of steel and compressive strength of concrete. The two components are often secured by shear connectors such as headed studs to prevent slippage and to maintain composite action. In spite of its popularity, very little research was conducted on steel-concrete composites particularly on headed stud shear connectors in regards to its post-fire behaviour. This research investigates the post-fire behaviour of innovative shear connectors for composite steel and concrete. Three type of connectors were investigated. They are conventional headed stud shear connectors, Blind Bolt 1 and Blind Bolt 2 blind bolts. Push-out test experimental studies were conducted to look at the behaviour and failure modes for each connector. Eighteen push tests were conducted according to Eurocode 4. The push test specimens were tested under ambient temperatures and post fire condition of 200°C, 400°C and 600°C. The results in ambient temperature are used to derive the residual strength of shear connectors after exposing to fire. Findings from this research will provide fundamental background in designing steel-concrete composites where there is danger of fire exposure.

1. INTRODUCTION

Steel-concrete composite beam/slab construction is common practice in bridges and multi-storey buildings due to the combination of compressive strength of concrete and tensile strength of steel (Heidarpour & Bradford 2010). The two components are often secured by shear connectors that greatly influence its strength and ductility (Mirza & Uy 2009). Despite its popularity in these type of constructions, composite members are still a subject of continuous development (Rodrigues & Laím 2011). One of the areas of interest in the development of composite structures is the shear connectors that bond concrete and steel (Rodrigues & Laím 2011). Interests in these developments are however limited due to the high cost in setting up in a laboratory environment (Ellobody & Young 2006). Even though the costs of these experiments are monumental, researchers still manage to set up experiments with good results such as conducted by Wang et al. (2013) and Alderighi and Salvatore (2009) in multi-level framed buildings.

A review of literature shows that research on steel-concrete composite structures has focused behaviour of push-out tests at ambient temperature and at elevated temperature. Push-out tests of composite structures at ambient temperature showed that their strength and ductility were often influenced by their material properties (Galjaard & Walraven 2001) (Ellobody & Young 2006). Galjaard and Walraven (2001) conducted push out tests for five different shear connectors: headed studs, continuous perfobondstrip, oscillating perfobondstrip, waveform strip and T-connector. Similarly, Baran and Topkaya (2012) conducted an experimental study on another type of shear connector: channel type shear connector or C-channel. The tests aim was to determine the strength of different sizes of C-channel as shear connector in steel-concrete composite structure (Baran & Topkaya 2012).

Push-out tests on steel-concrete composite structures utilising headed studs were also conducted at elevated temperatures by Zhao et al (2008), Mirza and Uy (2009), Anderson (2011), Wang (2012) and Imagawa et al (2012) among others. Push-out tests on steel-concrete composite structures utilising continuous perfobond strip (Rodrigues and Laím 2011) and T, T-block and T-perfobond (Rodrigues and Laím 2014) have also been conducted at elevated temperatures.

This paper focuses on the behaviour of steel-concrete composite structures using innovative shear connectors under post fire. Post-fire behaviour of steel-concrete composite structures is investigated with a focus on failure in push tests made up of three types of shear connectors; headed studs, Blind Bolt 1 and Blind Bolt 2. Eighteen push-out tests were carried out. The push-out tests were carried out at ambient temperature and post fire condition of 200°C, 400°C and 600°C. The results at ambient temperature are used to determine the residual strength of steel-concrete composite structures after exposure to fire.

2. EXPERIMENTAL STUDY

2.1. Experimental set-up and specimen

The test specimens were based on the Eurocode 4 standard and were fabricated in a similar manner as outlined in the standard. However, due to the size limitation of the furnace, all specimens were modified to fit in the furnace. The steel section adopted was a 200PFC and two 200PFC configured as shown in Figure 1. The width of the slabs for the specimens were also been downsized from 600mm specified by the Eurocode 4 to 400mm. The only exception is the reinforcing bars where all the bars were upsized to N12 (12mm diameter) instead of 10mm diameter specified in Eurocode 4. The spacing and size of the shear connectors were kept the same to the Eurocode 4 dimensions. Specimens using headed studs is shown in Figure 1(a). Specimens using Blind Bolt 1 and 2 bolts as shear connectors were also used and are shown in Figure 1(b) and 1(c) respectively.

(a) Specimen using headed stud shear connector

(b) Specimen using Blind Bolt 1

(c) Specimen using Blind Bolt 2

Figure 1. Push out test specimens using (a) headed stud shear connectors, (b) Blind Bolt 1 and (c) Blind Bolt 2

Push out tests of specimens using headed studs, Blind Bolt 1 and Blind Bolt 2 as shear connectors were carried out for specimens at ambient temperature and post fire condition of 200°C, 400°C and 600°C. The push out test followed the Eurocode 4 testing protocol although some ambient tests were also tested without the application of 25 cycles for comparison.

Following the Eurocode 4 push out test protocol, the load was applied in increments up to 40% of the expected failure load and then cycled 25 times between 5% and 40% of the expected failure load. The application of 25 loading cycles between 5% and 40% of the estimated failure load gives a response that is close to elastic but enables the specimen to settle and therefore stabilize for the loading to failure thereafter. Subsequent incremental loads were then applied to prevent the failure of the specimens in less than 15 minutes. In order to prevent the specimens from failing in less than 15 minutes, a loading rate of 0.01 mm/s was used. The loading rate of 0.01 mm/s ensures that the specimen will simulate a static loading condition. Part of the requirement for Eurocode 4 push test is to determine the relative slip between the steel and concrete continuously during loading. In order to achieve this requirement, linear variable displacement transducers (LVDT) were attached to the steel and the concrete (see Figure 2). Data of slip versus load was recorded and the failure modes noted. The data and failure modes at ambient temperature serve as the baseline for comparison with post-fire test specimens. The collection of data was ceased when the load dropped to 20% of the maximum load.

The preheating of all specimens subjected to post-fire analysis followed the ISO834 standard fire curve in obtaining the desired temperature. Prior to the preheating of the specimens, a 40% preload was applied to all the post-fire specimens to reflect the specimens service loading. A total of two specimens were heated at each temperature regime (200°C, 400°C, and 600°C) for every type of shear connector. In order to achieve the desired temperature, a temperature controlled furnace was used. The furnace uses three gas burners in heating the specimens with two on one side and one at the other. When the heating reached the desired temperature, heating was continued for 1 hour of soaking time before the furnace was switched off.

Figure 2. Push out test set up for ambient and post fire test specimens

The cooling process used in this experiment was the natural air cooling – leaving the specimen overnight to reach ambient temperature. The cooling method has an effect on residual compressive strength of concrete. Compressive strength loss is generally higher for rapid cooling or quenching using water compared to relatively slow cooling in air. Rapid cooling generally causes the development of detrimental micro-cracking as a result of temperature differentials between the outer and inner layers of concrete (Balendran et al 2001). The push out test procedure used to determine the residual strength of post fire specimens was the same as that for specimens tested at ambient temperature.

2.2. Material and Geometric Properties

Three types of shear connectors were used in this investigation; the headed studs, Blind Bolt 1 and Blind Bolt 2. The headed studs used have a diameter of 19mm, length of 100mm and ultimate tensile strength of 410MPa, while the Blind Bolt 1 used have a diameter of 20mm, length of 100mm and ultimate tensile strength of 390MPa. On the other hand, the Blind Bolt 2 bolts used have a diameter of 20mm, length of 100mm and ultimate tensile strength of 830MPa.

The 200PFC sections used in this investigation had flange width of 200mm, flange thickness of 12mm, web thickness of 6mm, yield strength of 300MPa and ultimate tensile strength of 440MPa. For fire protection, a hypercoating paint was used to provide a 2hr fire protection. The hypercoating paint was applied to all exposed steel section of the specimen after the removal of the formwork. In this experimental investigation, the time for the removal of formwork was 21 days after the concrete was cast.

The concrete used in the concrete slab had a 28day compressive strength of 30MPa and Young's Modulus of 36690MPa. The reinforcing bars used in the concrete slabs had a diameter of 12mm and yield strength of 500MPa.

3. RESULTS AND DISCUSSION

The three types of push out test specimens using headed studs, Blind Bolt 1 and Blind Bolt 2 were tested at ambient temperature and at post fire condition of 200°C, 400°C and 600°C. For each type of specimen, the specimens tested at ambient temperature were also tested by applying either 25 cycles as per EC4 testing protocol while others were tested without cyclic loading for comparison.

3.1. Behaviour of headed stud shear connector

Figure 3 shows the load-slip relationship for the headed stud shear connector specimens tested at ambient temperature under 25 and no cycles. Despite the cycle loading, headed studs that were tested under 25 cycles showed greater slip and loading capacity compared to the specimen that was tested with no cycle loading. However, both specimens experienced a sudden drop in load capacity due to concrete failure. The weaker compressive strength of concrete leading to concrete failure was the primary factor in the sudden drop of the load as shown in Figure 3.

Figure 3. Load –Slip relationship for headed stud shear connector specimens at ambient temperature

Failure modes of headed stud specimens at ambient temperature were mainly dominated by the concrete failure – splitting of the concrete slab as shown in Figure 4. This type of failure occurred because of the weaker compressive strength of concrete and therefore no yielding of the shear connector was observed. The specimens tested under 25 and no cycles showed similar failure modes, Figure 4.

(a) Specimen loaded to 25 Cycles

(b) Specimen with no cycles

Figure 4. Failure mode of headed stud shear connector specimens at ambient temperature

The post fire push out tests, for headed stud shear connector specimens were also carried out. Figure 5 shows the load versus slip graphs of the headed stud specimens at post fire condition of 200°C, 400°C and 600°C. A sudden drop in load is more evident in post-fire conditions of 200 and 400°C. Despite the low rigidity at the start of testing, the test at 200°C showed greater ductility and maximum load compared to the tests at 400°C and 600°C.

Headed shear studs post-fire 200, 400, and 600°C specimens all showed a similar type of failure mode as shown in Figure 6. All the post fire headed stud specimens failed through splitting of the concrete slab or concrete failure. The spalling of concrete after exposure to high temperature had a significant impact on the strength of concrete making the slab the weakest part of the steel-concrete composite specimens. After heating, the steel sections did not show any signs of deformation except the minor expansion of the fire protection coating. Minor cracks on the concrete slab were observed on most of the post fire headed stud specimens as part of the thermal damage caused by the fire. A separation between steel and concrete slab was also observed on some of the specimens prior to the testing.

Figure 5. Load –Slip relationship for headed stud shear connector specimens post fire

Figure 6. Failure mode of headed stud shear connector specimens post fire

3.2. Behaviour of Blind Bolt 1

Figure 7 shows the results of load versus slip for the Blind Bolt 1 specimens tested at ambient temperature under 25 cycles and no cycles respectively. As illustrated in Figure 7, the difference between two testing conditions was very minimal.

The push-out tests conducted for the Blind Bolt 1 specimens tested at ambient temperature failed through concrete failure as shown in Figure 8. The Blind Bolt 1 specimens showed a different concrete failure mode to the headed stud and Blind Bolt 2 specimens. Instead of splitting the concrete slab in half, the specimen failed by pulling out a portion of concrete closer to the steel section, see Figure 8. The possible cause of this type of failure mode may be due to the geometric arrangement at the end of the Blind bolt 1. The sleeve that secures the grip into the steel section of the Blind Bolt 1 forms petals which can create stress concentrations in the surrounding concrete.

Figure 7. Load –Slip relationship for Blind Bolt 1

(a) Specimen loaded to 25 Cycles

(b) Specimen with no cycles

Figure 8. Failure mode of Blind Bolt 1 specimens at ambient temperature

The post fire push out tests for Blind Bolt 1 specimens was also carried out. Figure 9 shows the load versus slip of the Blind Bolt 1 specimen push out tests at post fire condition of 200°C, 400°C and 600°C. The Blind Bolt 1 specimens that were tested tend to reach the ultimate capacity followed by

a drop in load before another increasing trend in loading before final failure. The ductility shown by all the specimens that were tested, is similar to the strain hardening phenomenon of steel. The post-fire 200°C and 400°C specimens showed greater ductility compared to specimen at post-fire condition of 600°C, see Figure 9.

The failure mode of Blind Bolt 1 specimens at post-fire conditions was due to concrete failure. However, all Blind Bolt 1 specimens tested at post-fire conditions of 200, 400, and 600°C failed due to the splitting of the concrete slab. This was unlike the concrete failure of the Blind Bolt 1 specimens at ambient temperature which tended to be localized at the position of a Blind Bolt 1. In general, the failure modes for the post fire Blind Bolt 1 specimens were mainly due to concrete failure and separation between the steel and the concrete as shown in Figure 10.

Figure 9. Load –Slip relationship for Blind Bolt 1 specimens post fire

Figure 10. Failure mode of Blind Bolt 1 connector specimens post fire

3.3.Behaviour of Blind Bolt 2

Figure 11 shows the load-slip relationship for the Blind Bolt 2 specimens tested at ambient temperature under 25 and no cycles. The specimen subjected to 25 cycles showed more stability and achieved a greater load and slip before failure.

Figure 12 shows the typical failure of the Blind Bolt 2 specimens tested at ambient temperature with 25 and no cycles. As illustrated in Figure 12 failure modes were mainly dominated by the concrete failure. The Blind Bolt 2 specimen subjected to 25 cycles showed yielding of the reinforcement bars which occurred when the splitting of the slab crossed the bars. This type of failure led to the higher maximum slip compared to the specimen tested without cycling.

Figure 11. Load –Slip relationship for Blind Bolt 2

(a) Specimen loaded to 25 Cycles

(b) Specimen with no cycles

Figure 12. Failure mode of Blind Bolt 2 specimens at ambient temperature

The push out tests for Blind Bolt 2 specimens was also carried out at post fire conditions of 200oC, 400°C and 600°C. Figure 13 shows the load versus slip of the Blind Bolt 2 specimens tested at post

fire conditions. The Blind Bolt 2 specimens tested showed a drop in load followed by a gradual increase in loading before a sudden drop in load. The loading capacity behaviour was similar to the strain hardening of a steel material in a tensile test. The ductility of the Blind Bolt 2 specimens was more evident at the post-fire condition of 200°C compared to post-fire conditions of 400 and 600°C.

The failure modes for all the Blind Bolt 2 specimens tested at post fire conditions of 200, 400, and 600°C were all concrete failures, see Figure 14. Furthermore, minor separation of steel and concrete was observed for post-fire 400° and 600°C before the test was conducted. The separation between the steel and concrete prior to the test was caused by the thermal expansion of the steel and the concrete which in turn resulted in a reduction in load capacity.

Figure 13. Load –Slip relationship for Blind Bolt 2 specimens post fire

Figure 14. Failure mode of Blind Bolt 2 connector specimens post fire

3.4. Comparison of Results at Ambient Temperature

Standards such as Eurocode 4, AISC (2005) and the Australian Standard AS2327.1-2003 can be used to predict strength of the shear connectors.

The failure load of a shear connector based on Eurocode 4 can be predicted using the lesser of Equations 1 and 2 as follows:

$$F_L = (0.29\alpha d^2 \sqrt{f_{ck} E_c}) \quad (1)$$

$$F_L = \left(0.8 f_u \frac{\pi d^2}{4}\right) \quad (2)$$

where,

α = modification factor, $0.2(h/d + 1) < 1.0$,

d = diameter of shear connector (mm)

h = 100mm

f_{ck} = concrete cylinder compressive strength (MPa)

E_c = static elastic modulus of concrete

f_u = ultimate tensile strength of the shear connector

F_L = failure load (N).

Equations 3 and 4 are used by the American Institute of Steel Construction, AISC (2005) to estimate the failure load of shear connectors. The lesser value of Equations 3 and 4 are used to predict the failure load of shear connector.

$$F_L = A_s f_u \quad (3)$$

$$F_L = 0.5 A_s \sqrt{f_{ck} E_c} \quad (4)$$

where,

F_L - failure Load (N)

A_s = shank cross sectional area of the shear connector (mm^2),

f_u = ultimate tensile strength of the shear connector (MPa)

f_{ck} = compressive strength of concrete (MPa)

E_c = elastic modulus of concrete (MPa)

Equations 5 and 6 are used by the Australian Standard AS2327.1-2003 (SAL 2003) to estimate the failure load of the shear connectors. The lesser value of Equations 5 and 6 are used to predict the failure load of shear connector.

$$F_L = 0.63 d^2 f_u \quad (5)$$

$$F_L = 0.31 d^2 \sqrt{f_{ck} E_c} \quad (6)$$

where,

F_L - failure Load (N)

d – shank diameter of the shear connector (mm),

f_u = ultimate tensile strength of the shear connector (MPa)

f_{ck} = compressive strength of concrete (MPa)

E_c = elastic modulus of concrete (MPa)

Table 1 shows the experimental failure loads as well as the predicted failure loads based on different standards for the push out tests at ambient temperature. Table 2 shows the ratios of the average test load to predicted failure loads for push out test specimens using different shear connectors at ambient temperature.

From Tables 1 and 2, AISC (2005) significantly overestimated the failure capacity of all the shear connectors in the push out test specimens, as shown by the average ratio of test failure load to predicted failure load in Table 2. Eurocode 4 and the Australian standard were comparatively better in predicting the failure capacity of the different shear connectors.

Based on the materials properties, the American standard, AISC (2005), Australian Standard (SAL 2003) and Eurocode 4 see Table 1, predicted failure of the headed studs and Blind Bolt 1 to be dominated by the shear connector failure (i.e. Equation 2, 3 and 5 had the lesser value). The predicted failure mode for the headed studs and Blind Bolt 1 by the standards contradicts the failure mode observed in the specimens. Most of the specimens tested failed by concrete failure – splitting of the section of concrete around the shear connector and through the specimen.

Based on theoretical analysis of Eurocode 4, AISC (2005) and AS2327.1-2003, all three standards correctly predicted the failure mode of Blind Bolt 2 specimens as concrete failure. Despite the correctly predicted failure mode, the standards predicted failure loads are considerably different to the experimental test failure loads.

Based on the analysis of the predictions by the three different standards (Eurocode 4, AISC 2005, and AS2327.1-2003), Eurocode 4 followed by the Australian Standard can be considered to be reasonable in predicting the shear capacity of all the specimens tested at ambient temperature (see

Table 2). From the result of this analysis Eurocode 4 can be considered to be a more reliable basis for determining the residual strength in post-fire analysis.

Table 1. Test and Predicted Failure Loads for push out test specimens using different shear connectors.

Shear Connectors	Test 25 Cyc. (kN)	Test No Cyc. (kN)	EC4 (kN)	AISC 2005 (kN)	SAL 2003 (kN)
Headed Stud	778	688	744#	930#	746#
Blind Bolt 1	601	626	784#	980#	786#
Blind Bolt 2	712	629	974©	1318©	1040©

- Shear connector failure predicted by standard

© - Concrete crushing predicted by standard

Table 2. Ratios of Average Test to Predicted Failure Loads for push out test specimens using different shear connectors.

Shear Connectors	Average Load/EC4 Predicted Load	Average Load/AISC Predicted Load	Average Load/SAL Predicted Load
Headed Stud	0.99	0.79	0.98
Blind Bolt 1	0.78	0.63	0.78
Blind Bolt 2	0.69	0.51	0.64
Mean Ratio	0.82	0.64	0.80

3.5.Comparison of Results at Post Fire

Table 3 shows the summary of test results for headed stud specimens. Table 3 shows the test failure loads, average test failure loads and residual strength for the headed studs specimens tested at ambient temperature and post-fire conditions of 200, 400 and 600°C. The residual strength, defined as the ratio of the average failure load for post-fire specimens to average failure load for ambient temperature specimens indicated that 25, 43, and 60% loss in load capacity were reached for post-fire conditions of 200, 400, and 600°C respectively.

Table 3. Comparison of Headed studs test results for ambient and post-fire.

Temperature(°C)	Test Failure Load (kN)	Average Test Failure Load (kN)	Residual Strength
Ambient 25 Cycles	809	750	1.00
Ambient No Cycles	691		
Post-fire 200 - 01	561	561	0.75
Post-fire 200 - 02			
Post-fire 400 - 01	389	426	0.57
Post-fire 400 - 02	463		
Post-fire 600 - 01	314	297	0.40
Post-fire 600 - 02	280		

Table 4 shows the test results for Blind Bolt 2 specimens tested at ambient and post-fire. From Table 4, the residual strengths for the Blind Bolt 2 had dropped on average by 33, 56, and 63% for post-fire conditions of 200, 400, and 600° Celsius respectively.

The summary of the loading capacity of Blind Bolt 1 specimens ambient and at post-fire condition of 200, 400, and 600°C is shown in Table 5. From Table 5, the ambient temperature loading capacity was the baseline for all post-fire analysis. For the post-fire condition of 200°C, a 33% drop in loading capacity was observed; similar to the result obtained from the Blind Bolt 2 (see Table 4). For Blind Bolt 1 bolt specimens at post-fire conditions of 400 and 600° Celsius, the load capacities dropped by 57 and 66% respectively.

Table 4. Comparison of Blind Bolt 2 test results for ambient and post-fire.

Temperature (°C)	Test Failure Load (kN)	Average Test Failure Load (kN)	Residual Strength
Ambient 25 Cycles	765	710	1.00
Ambient No Cycles	654		
Post-fire 200 - 01	464	478	0.67
Post-fire 200 - 02	491		
Post-fire 400 - 01	265	311	0.44
Post-fire 400 - 02	357		
Post-fire 600 - 01	298	265	0.37
Post-fire 600 - 02	232		

Table 5. Comparison of Blind Bolt 1 test results for ambient and post-fire.

Temperature (°C)	Test Failure Load (kN)	Average Test Failure Load (kN)	Residual Strength
Ambient 25 Cycles	597	611	1.00
Ambient No Cycles	625		
Post-fire 200 - 01	474	407	0.67
Post-fire 200 - 02	340		
Post-fire 400 - 01	278	261	0.43
Post-fire 400 - 02	244		
Post-fire 600 - 01	191	208	0.34
Post-fire 600 - 02	224		

4. CONCLUSIONS

The behaviour of headed studs, Blind Bolt 1 and Blind Bolt 2 as shear connectors at both ambient temperature and post-fire condition were tested using the push-out test specimens. Additionally, the experimentally determined test failure loads were compared to the theoretically predicted failure loads using the Eurocode 4, AISC (2005) and AS2327.1-2003 method of analysis. The results of the experimental tests showed that all specimens were dominated by the concrete failure of the slab at

both ambient temperature and at post-fire. The following observations were made based on the experimental tests and comparison with predictions from the current standards:

1. The experimental test failure loads of headed studs and Blind Bolt 2 specimens, at ambient temperature, were of the same magnitude. Blind Bolt 1 specimens, however, showed less failure capacity due to the stress concentrations around the casing of the bolts.
2. Headed studs performed well compared to Blind Bolt 1 and 2 at ambient temperature and all post-fire target temperatures. On the other hand, Blind Bolt 2 performed better than Blind Bolt 1 at ambient temperature and all post-fire target temperatures.
3. The residual strength of the headed studs in all post-fire target temperatures was better compared to the Blind Bolt 1 and 2. When compared to the failure loads at ambient temperature, the residual strength of Blind Bolt 1 and Blind Bolt 2 are comparable at all post fire target temperatures.
4. Following exposure to various degrees of temperatures, all the specimens exhibited minor structural damage, with slight separation of the steel and concrete evident and minor spalling. However, thermal damage to the specimen causes the concrete to become brittle. As a consequence, a sudden drop in load was observed for all specimens at post-fire.
5. For the 30MPa strength of concrete used for all specimens, the eight shear connectors per specimen had greater shear strength compared to concrete. Therefore, no shear connector yield failure was observed at both ambient temperature and at post-fire.

ACKNOWLEDGEMENTS

This project was sponsored by the Advanced Materials and Smart Structures (AMSS) Research Group and University of Western Sydney Research Grant Scheme (RGS). The authors wish to

thank the technical support of Dr Mithra Fernando, Mr Robert Marshall, Mr Murray Bolden and Mr Mitch Quirk.

REFERENCES

- Alderighi, E & Salvatore, W 2009, 'Structural fire performance of earthquake-resistant composite steel–concrete frames', *Engineering Structures*, vol. 31, no. 4, pp. 894-909.
- Anderson, K 2011, 'THE EFFECTS OF CONNECTIONS ON STRUCTURAL BEHAVIOUR IN FIRE', Postgraduate Thesis thesis, Phd thesis, The University of Edinburgh.
- Baran, E & Topkaya, C 2012, 'An experimental study on channel type shear connectors', *Journal of Constructional Steel Research*, vol. 74, no. 0, pp. 108-17.
- AISC 2005, Specification for Structural Steel Buildings, ANSI/AISC 360-05, American Institute of Steel Construction, Chicago, Illinois 60601-1802
- Balendran B.V., Maqsood T. and Nadeem A. 'Effect of cooling method on residual compressive strength of high strength concrete cured for 28 days and 180 days and heated to elevated temperatures', 26th Conference on OUR WORLD IN CONCRETE & STRUCTURES: 27 - 28 August 2001, Singapore, Article Online Id: 100026018, Singapore Concrete Institute, <http://cipremier.com/100026018>
- Ellobody, E & Young, B 2006, 'Performance of shear connection in composite beams with profiled steel sheeting', *Journal of Constructional Steel Research*, vol. 62, no. 7, pp. 682-94.
- Eurocode 4 2004, EN 1994-1-2: - Design of composite steel and concrete structures - Part 1-2: General rules - Structural fire design
- Galjaard, HJC & Walraven, JC 2001, 'Behaviour of Different Types of Shear Connectors for Steel-Concrete Structures', in A Zingoni (ed.), *Structural Engineering, Mechanics and Computation*, Elsevier Science, Oxford, pp. 385-92.

- Heidarpour, A & Bradford, MA 2010, 'Nonlinear Analysis of Composite Beams with Partial Interaction in Steel Frame Structures at Elevated Temperature', *Journal of Structural Engineering*, vol. 136, no. 8, pp. 968-77.
- Imagawa, Y, Ohyama, O & Kurita, A 2012, 'Mechanical Properties of Shear Stud during and after Fire', *Struct. Eng. Int.*, vol. 22, no. 4, pp. 487-92.
- Mirza, O & Uy, B 2009, 'Behaviour of headed stud shear connectors for composite steel–concrete beams at elevated temperatures', *Journal of Constructional Steel Research*, vol. 65, no. 3, pp. 662-74.
- Rodrigues, JPC & Laím, L 2011, 'Behaviour of Perfobond shear connectors at high temperatures', *Engineering Structures*, vol. 33, no. 10, pp. 2744-53.
- Rodrigues, JPC & Laím, L 2014, 'Experimental investigation on the structural response of T, T-block and T-Perfobond shear connectors at elevated temperatures', *Engineering Structures*, vol. 75, no. 0, pp. 299-314.
- SAL 2003. Australian Standard AS2327.01-2003, Composite Structures, Part 1 Simply Supported Beams, Standards Australia Limited, Sydney, Australia.
- Wang, AJ 2011, 'Studies on semi-continuous composite beams with non-uniform fire protection', *Australian Journal of Structural Engineering*, vol. 13, no. 1, 2012/01//, p. 29+.
- Wang, Y, Dong, YL, Li, B & Zhou, GC 2013, 'A fire test on continuous reinforced concrete slabs in a full-scale multi-story steel-framed building', *Fire Safety Journal*, vol. 61, no. 0, pp. 232-42.