

# The University of Bradford Institutional Repository

<http://bradscholars.brad.ac.uk>

This work is made available online in accordance with publisher policies. Please refer to the repository record for this item and our Policy Document available from the repository home page for further information.

To see the final version of this work please visit the publisher's website. Access to the published online version may require a subscription.

**Link to publisher's version:** <http://dx.doi.org/10.1002/adhm.201300518>

**Citation:** Hook AL, Chang C, Scurr DJ et al (2014) Thermally switchable polymers achieve controlled *Escherichia coli* detachment. *Advanced Healthcare Materials*. 3(7): 1020-1025.

**Copyright statement:** © 2014 The Authors. Published by WILEY-VCH Verlag GmbH & Co. KGaA, Weinheim. This is an open access article under the terms of the *Creative Commons Attribution* License, which permits use, distribution and reproduction in any medium, provided the original work is properly cited.

# Thermally Switchable Polymers Achieve Controlled *Escherichia coli* Detachment

Andrew L. Hook, Chien-Yi Chang, David J. Scurr, Robert Langer, Daniel G. Anderson, Paul Williams, Martyn C. Davies, and Morgan R. Alexander\*

Biofilms develop from the initial surface attachment of bacteria to structured “slime cities” within which bacteria are up to 1000 times more resistant to antibiotic treatment.<sup>[1]</sup> Biofilms can cause failure for a wide range of medical devices including urinary and venous catheters.<sup>[1]</sup> Impaired device function is also associated with biofilm formation on water filters and ship hulls.<sup>[2,3]</sup> Controlling bacterial biofilms remains a key aim across many disciplines. One strategy to achieve this is the use of switchable materials<sup>[4,5]</sup> to trigger the removal of biofilms from surfaces,<sup>[6–10]</sup> which would enable intermittent “cleaning” of surfaces or filters. In this study, we apply two switchable materials to achieve up to 96% detachment of a uropathogenic *Escherichia coli* (UPEC) strain upon a reduction in temperature. Furthermore, an assessment of the changes in surface chemistry of the switchable materials following the temperature switch provides new insights into bacteria–surface interactions, which are important for understanding polymer surface resistance to bacterial attachment. Specifically, we demonstrate that the bacterial attachment cannot be explained by a simple correlation with water contact angle (WCA).

Two polymer samples were selected from a number of switchable materials discovered using a combinatorial screen of polyacrylates.<sup>[11]</sup> These two materials exhibited the largest increase or decrease in WCA when the temperature was reduced from all materials in the screened library.<sup>[11]</sup> The first co-polymer, which exhibited a decrease in WCA with a reduction in temperature,

was a 70:30 cross-linked copolymer of poly(propylene glycol) diacrylate (PPGdA) and trimethylolpropane ethoxylate (1 EO/OH) methyl ether diacrylate (TMPEMEDA), which will be referred to as PPGdA 70:30 TMPEMEDA. The chemical structures of the monomers are shown in **Figure 1a**. The second material, which exhibited an increase in WCA with a reduction in temperature, was a linear 70:30 copolymer of 2-[[[(butylamino)carbonyl]oxy]ethyl acrylate (BACOEAE) and 2-(2-methoxyethoxy)ethyl methacrylate (MEEMA), which will be referred to as BACOEAE 70:30 MEEMA. In addition, homopolymers of the four monomer components were prepared for comparison. Polymers were prepared using a photo-initiated free radical polymerization mechanism similar to the on slide polymerization utilized by the high-throughput materials discovery methodology.<sup>[11,12]</sup> Glass was used as a non-thermally responsive control.

To allow for bacterial attachment and subsequent biofilm formation PPGdA 70:30 TMPEMEDA and BACOEAE 70:30 MEEMA were inoculated with strains of UPEC (strain 536), *Pseudomonas aeruginosa* (strain PAO1) or *Staphylococcus aureus* strain (8325-4). *E. coli* is a significant cause of water contamination<sup>[13]</sup> and all three bacterial species are responsible for significant levels of human infection.<sup>[14,15]</sup> The polymers and bacteria were incubated for 72 h at 37 °C, above the switching temperature of the polymers,<sup>[11]</sup> in protein-free media (RPMI) prior to a 4-h incubation at either 4 °C (below the switching temperature of the polymers<sup>[11]</sup>) or 37 °C. Bacterial surface coverage was determined by staining the washed polymers with SYTO17 and quantifying the fluorescence output, as previously described.<sup>[16]</sup> Representative confocal microscopy images of bacteria on the polymers when the incubation was maintained at 37 °C are contrasted with those where it was reduced to 4 °C (see **Figure 1b,c** for PPGdA 70:30 TMPEMEDA and BACOEAE 70:30 MEEMA, respectively). **Figure 1d** shows the quantification of UPEC surface coverage on the homopolymer and glass surfaces. The morphology of the bacterial biofilms on the two materials differed; on BACOEAE 70:30 MEEMA fewer but larger colonies were observed (**Figure 1b**) while on PPGdA 70:30 TMPEMEDA, a larger number of smaller colonies were observed (**Figure 1c**). Upon a reduction in temperature to 4 °C, both PPGdA 70:30 TMPEMEDA and BACOEAE 70:30 MEEMA showed a significant decrease in bacterial attachment (compared **Figure 1b,c** right hand panels). On PPGdA 70:30 TMPEMEDA, bacterial coverage was reduced from 2.0% to 0.10%, corresponding to the release of 96% of the attached bacteria, while on BACOEAE 70:30 MEEMA bacterial coverage was reduced from 5.3% to 1.0%, corresponding to the release of 81% of attached bacteria (**Figure 1d**). A bacterial coverage of 0.05% after 72 h incubation was observed on the polymer from our recently discovered new class of materials resistant to bacterial attachment with the best

Dr. A. L. Hook, Dr. D. J. Scurr, Prof. M. C. Davies,  
Prof. M. R. Alexander

Laboratory of Biophysics and Surface Analysis,  
School of Pharmacy  
University of Nottingham  
Nottingham NG72RD, UK

E-mail: Morgan.Alexander@nottingham.ac.uk

Dr. C.-Y. Chang, Prof. P. Williams

School of Life Sciences  
University of Nottingham  
Nottingham NG72RD, UK


Prof. R. Langer, Prof. D. G. Anderson  
Department of Chemical Engineering  
Harvard-MIT Division of Health Sciences and Technology  
77 Massachusetts Avenue, Cambridge, MA 02139, USA

Prof. R. Langer, Prof. D. G. Anderson  
David H. Koch  
Institute for Integrative Cancer Research  
Massachusetts Institute of Technology  
500 Main Street, Cambridge, MA 02139, USA

This is an open access article under the terms of the Creative Commons Attribution License, which permits use, distribution and reproduction in any medium, provided the original work is properly cited.

DOI: 10.1002/adhm.201300518





**Figure 1.** a) Chemical structures of monomers. b,c) Confocal images of SYTO17-stained UPEC on b) PPGdA 70 :30 TMPEMEdA or c) BACOEa 70:30 MEEMA at 37 °C (left) and 4 °C (right). Each image is 160 × 160 μm. Images from controls are shown in Figure S11 (Supporting Information).


resistance to UPEC.<sup>[17]</sup> No switchable detachment was observed for either *P. aeruginosa* or *S. aureus* (data not shown) suggesting the thermally induced release of bacteria may be specific for *E. coli*. Previously, the release of up to 98% of *Halomonas marina* and *Staphylococcus epidermidis* attached to the polymer poly(*N*-isopropyl acrylamide) (PNIPAAm) was achieved by lowering the temperature of PNIPAAm to below its lower critical solution temperature.<sup>[18]</sup>

In our studies, low UPEC coverage was observed on the homopolymer of TMPEMEdA, PPGdA, and BACOEa at both temperatures, with bacterial coverage measured in the range of 0.1%–0.3%. Only the homopolymer of MEEMA showed a significant ( $p < 0.37$ ) change in bacterial coverage with a change in temperature (Figure 1d). For this material, bacterial coverage increased from 0.3% to 0.9% with a reduction in temperature. An increase in WCA of 7° was observed for the homopolymer of MEEMA (Figure 2a), and for this case, an increase in hydrophobicity resulted in an increase rather than a reduction in bacterial attachment. The bacterial coverage on glass was 53% at 37 °C, which was not significantly different ( $p < 0.90$ ) to that at 4 °C, 58%.

Bacterial cells adapt rapidly to physicochemical changes in their growth environment including temperature and hence a reduction from 37 to 4 °C will induce a cold adaptive response. In *E. coli*, almost 300 genes showed differential expression when the temperature was reduced from 37 to 23 °C.<sup>[19]</sup> Hence, it is possible that the reduced attachment/detachment of the *E. coli* strain used in these studies to PPGdA 70:30 TMPEMEdA and BACOEa 70:30 MEEMA, respectively, is a consequence of the microbe's response to temperature rather than to any changes in the bacteria–material interaction. However, since we observed no differences in the surface coverage of *E. coli* on glass at 4 °C compared with 37 °C (Figure S11e, Supporting Information), we conclude that changes observed are indeed due to modification of the bacteria–polymer interactions.

The monomer constituents of the two switchable copolymers acted synergistically to produce a biological response that would not be predicted based upon the response observed for the respective homopolymers. For PPGdA 70:30 TMPEMEdA, the combination of monomer constituents supported much higher bacterial attachment at 37 °C than was observed for the homopolymers of PPGdA and TMPEMEdA. For BACOEa 70:30 MEEMA, the combination of the two monomers resulted in an increase in bacterial attachment at 37 °C that was reversible upon a reduction in temperature. This switch was not observed for the respective homopolymers. At 4 °C, the bacterial coverage of the PPGdA 70:30 TMPEMEdA (0.01%) was lower than the coverage on the homopolymers of PPGdA (0.14%) and TMPEMEdA (0.23%), while the bacterial coverage at 4 °C for BACOEa 70:30 MEEMA (1.0%) was similar to the homopolymer of MEEMA (0.9%), but higher than the homopolymer of BACOEa (0.2%).

d) Coverage of UPEC on polymer coupons or a glass coverslip grown at 37 °C (■) and grown at 37 °C then incubated at 4 °C (■) for 4 h. Error bars equal ± one standard deviation,  $n = 3$ . The coverage of bacteria on homopolymers of the four monomers after 72 h incubation is also shown. e) By analysis of the supernatant and sonication of the substrates, the total number of bacterial cells on the substrate (■) and in the supernatant (■) on glass or PPGdA 70:30 TMPEMEdA, respectively, was determined when either maintaining the temperature at 37 °C or reducing it to 4 °C.



**Figure 2.** a) WCA at both 40 °C (■) and 10 °C (■). Error bars equal  $\pm$  one standard deviation unit,  $n = 9$ . WCA measurements of b) PPGdA 70:30 TMPEMEdA and c) BACOEA 70:30 MEEMA and homopolymers d) PPGdA and e) BACOEA taken at 10 and 40 °C. The temperature of the materials was changed between the 10 and 40 °C three times. The error bars equal  $\pm 1$  standard deviation,  $n = 9$ .

To confirm that the bacterial cells were being released into the supernatant, total bacterial numbers were determined for both the supernatant and the substrate for PPGdA 70:30 TMPEMEdA before and after a temperature reduction. Cells were released from the coating by sonication before counting. After 4 h incubation at 37 °C, approximately 70% of the seeded bacteria remained on the surface while 30% of the bacteria were present in the supernatant for both the polymer and glass (Figure 1e). Dispersal occurs naturally in mature bacterial biofilms but may be triggered by different environmental cues including nutrient levels, oxygen tension, temperature, and bacterial signal molecules.<sup>[20]</sup> In our experiments, the consistent release observed from both glass and polymer at 37 °C suggests that these particular surfaces do not influence dispersal. When the sample temperatures were reduced the percentage of bacteria attached to the glass sample decreased to 63% with a corresponding increase in planktonic bacteria within the supernatant (Figure 1e). This suggests an increase in bacteria dispersal from biofilm at the low temperature compared with higher temperature. In *Neisseria subflava* and several other oral bacteria, a temperature-dependent dispersal pattern from a cool medium towards a warm medium has been observed.<sup>[21]</sup> The possible mechanism involved in driving-temperature-dependent dispersal is likely to depend on the intracellular levels of the second messenger cyclic diguanylate, which controls the balance between a sessile-surface-attached lifestyle and a free living planktonic lifestyle.<sup>[20]</sup>

On PPGdA 70:30 TMPEMEdA, a significant release of bacteria from the surface was observed, with the proportion of

bacteria in the supernatant increasing from 28% to 69% and the number of bacteria on the surface correspondingly reduced from 72% to 31% (Figure 1e). This equates to the release of 59% of the attached bacteria upon the reduction of temperature, confirming that bacteria are released from the surface of the polymer into the supernatant. The difference in the magnitude of the proportion of released bacteria between total cell counts and confocal microscopy methods is due to the different parameters being measured. In particular, the surface coverage measurements obtained via confocal microscopy do not resolve individual surface-attached bacterial cells especially within biofilms.

The surface properties of the polymers, as measured by time-of-flight secondary ion mass spectrometry (ToF-SIMS) and surface wettability analysis, were assessed to provide insight into the surface chemical changes associated with the bacterial release. Both PPGdA 70:30 TMPEMEdA and BACOEA 70:30 MEEMA showed a reversible switch in WCA (Figure 2a–c), with an average change in WCA of  $-10^\circ \pm 1^\circ$  and  $19^\circ \pm 5^\circ$ , respectively, when the temperature was reduced from 40 °C (above the switching temperature of the polymers<sup>[11]</sup>) to 10 °C (below the switching temperature of the polymers<sup>[11]</sup>). The glass transition temperature of the polymers was not in this range (Figure SI2, Supporting Information). A similar reversible switch in WCA was observed for the homopolymers of PPGdA and BACOEA (Figure 2d,e). No statistically significant change ( $p < 0.90$ ) in the WCA was measured on glass upon dropping the temperature (Figure 2a). Upon reduction in temperature below 37 °C, a decrease in WCA of  $15^\circ$  from  $60^\circ$  to  $45^\circ$  has

been previously observed for PNIPAAm,<sup>[18]</sup> and a decrease of 5° from 55° to 50° has been observed for an ethylene-glycol-based switchable surface.<sup>[22]</sup>

For ToF-SIMS analysis, the two switchable copolymers were introduced to the spectrometer at room temperature, cooled, and analyzed at -5 °C before warming to 37 °C and reanalyzing. Samples were held at a temperature for at least 1 h before analysis. The reversibility of any switches was also assessed (Figure S13 and 4, Supporting Information). These experiments were performed in vacuum, thus, any switching in the polymer surface structure is unlikely to occur by the same mechanism as when in a solvent. However, any changes in surface composition observed by ToF-SIMS may provide insight into the molecular mobility within the polymer and thus, can inform how any changes to the polymer surface may occur in water.

The relative change in each of the hundreds of secondary ions in the positive and negative spectra was calculated and when this change was statistically significant across three replicates ( $p < 0.05$ ), the ions with the largest (either negative or positive) change in intensity were identified, shown in Table S11 (Supporting Information) for PPGdA 70:30 TPPEMEDA and BACOE A 70:30 MEEMA. For reference, the intensities of each of these ions measured from the homopolymers of each material's monomer constituents are also shown. ToF-SIMS spectra of the two copolymers at -5 and 37 °C as well as the homopolymer controls are shown in Figures S15 and 6 (Supporting Information). X-ray photoelectron spectroscopy (XPS) was also used to quantify the surface chemistry of the two switchable polymers (Table S12, Supporting Information).

The secondary ions with the largest positive change in intensity on reduction of temperature on PPGdA 70:30 TPPEMEDA, and were therefore surface enriched at -5 °C, were all hydrocarbon fragment ions. The switching of these ions was partially reversible. These secondary ions were not specific to one monomer and likely originate from polymer backbone environments common to both monomers. The secondary ions with the largest negative change in intensity, which indicates surface enrichment at an elevated sample temperature, were associated with PPGdA by comparison of the homopolymer spectra of TPPEMEDA and PPGdA (Table S11, Supporting Information). The switching of these ions was nonreversible. There was no significant difference between the oxygen/carbon ratio as measured by XPS compared with the value calculated from the molecular structure of this polymer (Table S12, Supporting Information).

The secondary ions that increased in intensity on BACOE A 70:30 MEEMA when the temperature was elevated originated from both monomer components. Ions associated with MEEMA switched reversibly. The secondary ions with the largest reduction in intensity when the temperature was raised were all at a higher intensity in the homopolymer of MEEMA compared with the homopolymer of BACOE A and thus likely originate from MEEMA (Table S11, Supporting Information).

A number of studies have previously explored reversible bacterial attachment on switchable materials.<sup>[6,7,18]</sup> In all these cases, initial bacterial attachment occurred on materials with a WCA in the range of 50–70°, and bacterial release was triggered by a decrease in WCA brought on by a reduction in temperature. In this study, bacterial attachment occurred when the

WCA of the materials was in the range of 53°–56°; however, bacterial release was induced when the WCA was switched either above or below this range upon the reduction of temperature. This suggests that bacterial attachment cannot be explained by a simple correlation with WCA. Consistent with this observation, resistance to bacterial attachment has been observed previously on both superhydrophobic and superhydrophilic surfaces.<sup>[23,24]</sup>

Our data suggests that the surface composition of the polymers in this study plays the key role. For PPGdA 70:30 TPPEMEDA, ToF-SIMS analysis identifies that the PG moieties of PPGdA are surface enriched at 37 °C while the polymer backbone becomes preferentially exposed at reduced temperature with an accompanying decrease in the abundance of PG groups. The WCA analysis suggests that the polymer's hydrophilicity and potentially its solvation increased with a reduction in temperature. Together, these results suggest that at 37 °C and in solution the PPG side groups are collapsed, resulting in the PG moiety covering the surface and thus reducing the surface density of TPPEMEDA. However, at 4 °C, the polymer absorbs water, resulting in the extension of the polymer's side groups. This causes the bacteria to detach. This is a similar mechanism to that proposed for the switchable behavior of PNIPAAm,<sup>[25]</sup> ethylene glycol, and PG-based materials.<sup>[26]</sup>

For BACOE A 70:30 MEEMA, ToF-SIMS analysis suggests the surface enrichment of MEEMA at 37 °C, suggesting that the side groups are extended and possibly solvated. This is supported by the comparatively low WCA of the material at 37 °C. Large hydrocarbon fragments were detected for BACOE A 70:30 MEEMA using ToF-SIMS (Table S11, Supporting Information), such as  $C_9H_{20}^+$ , that are presumably derived from the polymer backbone. This is supported by the comparatively lower O/C ratio as measured by XPS (0.32) compared with the value calculated from the molecular structure of this polymer (0.41) (Table S12, Supporting Information). These fragments were also observed for the homopolymer of MEEMA, suggesting that the polymer BACOE A 70:30 MEEMA contains sections with repeated MEEMA units at its surface. The bacteria may have a specific affinity for the pendant group of MEEMA through hydrogen bonding of surface carbohydrates. Upon lowering of the temperature as the surface concentration of MEEMA is reduced the bacteria are released. The inclusion of BACOE A creates a surface more permissible for cell attachment at 37 °C.

In summary, two co-polymers previously identified by high-throughput screening to have thermoresponsive properties have been found to cause the detachment of UPEC by up to 96% when the temperature is reduced from 37 to 4 °C. The two polymers selected for this study were chosen because one exhibited an increase and the other a decrease in WCA when the temperature was dropped. The equivalent response of bacteria to these two materials despite their disparate change in WCA demonstrates that bacterial attachment cannot be explained by a simple correlation with WCA. This insight is important for understanding the mechanisms governing antifouling properties against bacterial attachment. ToF-SIMS and WCA analysis highlighted changes in the polymers' surface chemistry that accompanied the detachment of *E. coli*, suggesting that the polymers both undergo conformationally driven surface chemical changes when the temperature is altered. The switchable

polymer strategy utilized in this study could be applied for a variety of uses including self-cleaning bacterial filtration systems.

## Experimental Section

**Preparation of Polymer Samples:** Polymer coupons (10 mm diameter) were prepared by casting 5  $\mu\text{L}$  of monomer solution [75% ( $\text{v v}^{-1}$ ) monomer, 25% ( $\text{v v}^{-1}$ ) dimethyl formamide (DMF), and 1% ( $\text{w v}^{-1}$ ) 2,2-dimethoxy-2-phenyl acetophenone] onto epoxy-functionalized slides (Xenopore), previously dip-coated into 4% ( $\text{w v}^{-1}$ ) poly(2-hydroxyethyl methacrylate) in ethanol. Samples were irradiated with a long-wave UV source for 10 min,  $\text{O}_2 < 2000$  ppm. Samples were dried at  $<50$  mTorr for 7 d. The monomers used were 2-(2-methoxyethoxy)ethyl methacrylate, 2-[[butylamino]carbonyloxy]ethyl acrylate, poly(propylene glycol) diacrylate, and trimethylolpropane ethoxylate (1 EO/OH) methyl ether diacrylate (Sigma).

**Bacterial Attachment Assay:** UPEC strain 536, *P. aeruginosa* PAO1, and *S. aureus* 8325-4<sup>[6]</sup> were routinely grown on LB (Luria-Bertani, Oxoid, UK) agar plates at 37 °C. Prior to incubation with the bacteria, the polymer coupons were washed in distilled  $\text{H}_2\text{O}$  for 10 min, UV sterilized, and air-dried. Samples were incubated in 15 mL RPMI-1640 medium (Sigma) inoculated with bacteria ( $\text{OD}_{600} = 0.01$ ) from overnight cultures and grown at 37 °C with 60 rpm shaking for 72 h. One set of coupons ( $n = 3$ ) was then transferred to a 4 °C incubator, while another set ( $n = 3$ ) was maintained at 37 °C for a further 4 h. The coupons were then washed three times with 15 mL phosphate buffered saline (PBS, Oxoid, UK) for 5 min, stained with  $20 \times 10^{-6}$  M SYTO17 dye (Invitrogen, UK) for 30 min, dried, and then examined using a Carl Zeiss LSM 700 Laser Scanning Microscope with ZEN 2009 imaging software (Carl Zeiss, Germany). Bacterial surface coverage was analyzed using open source Image J 1.44 software (National Institute of Health, US).

To calculate the percentage of bacteria released from the polymer surface, a similar method was performed as above. Briefly, after 72 h incubation in bacterial culture, coupons were removed and washed three times with 15 mL PBS (Oxoid, UK) for 5 min. One set of coupons ( $n = 3$ ) was transferred to 2 mL PBS with 0.2% ( $\text{w v}^{-1}$ ) D-(+)-glucose (Sigma) at 4 °C for 4 h, while another set of coupons ( $n = 3$ ) were transferred to the 2 mL PBS/glucose solution and maintained at 37 °C for 4 h. Both surface adherent and aggregated bacteria were released and dispersed by sonication in PBS/glucose solution on ice five times for 10 s at 20% output power of W-380 Sonicator (Heat Systems-ultrasonics Inc.), followed by vortexing at maximum velocity for 15 s at room temperature. The sonication procedure did not adversely affect bacterial viability as confirmed by plating samples of bacterial liquid cultures before and after sonication. The bacterial cell numbers were determined using a Z30000 Helber Counting Chamber (Hawksley, UK) in conjunction with a Carl Zeiss Axio Observer phase contrast microscope (Carl Zeiss, Germany).

**Polymer Characterization:** Picolitre volume sessile WCA measurements were made on each polymer as previously described.<sup>[27]</sup> The temperature of an aluminum stage was regulated using a FBC 735 Temperature Controller (Fisherbrand) and held the samples ( $n = 9$ ) at a constant temperature for 120 min before WCA measurements were taken using a piezo picolitre-dosing instrument (Krüss DSA100). The ToF-SIMS analysis was performed on an ION-TOF IV instrument (IONTOF GmbH, Münster, Germany) fitted with a heating and cooling stage. Measurements of independent samples ( $n = 3$ ) were taken at temperatures of  $-5$  °C and 40 °C. A pulsed 25-kV  $\text{Bi}_3^+$  primary ion source was used at a target current of approximately 1 pA to raster two randomly selected  $100 \times 100$   $\mu\text{m}$  areas of the coupon to collect both positive and negative secondary ions. Charge compensation of the samples was accomplished with a pulsed electron flood gun. The mass of secondary ions was determined using a time-of-flight mass analyzer. The typical mass resolution (at  $mz^{-1}$  41) was just over 6000. XPS was carried out on a Kratos Axis Ultra instrument using monochromated Al  $K\alpha$  radiation (1486.6 eV), 15 mA emission current, 10 kV anode

potential, and a charge-compensating electron flood. High-resolution core levels were acquired at a pass energy of 20 eV. The takeoff angle of the photoelectron analyzer was 90°. All spectra were acquired using an aperture of 110 mm diameter.

## Supporting Information

Supporting Information is available from the Wiley Online Library or from the author.

## Acknowledgements

Funding from the Wellcome Trust (grant number 085245) and the NIH (grant number R01 DE016516) is kindly acknowledged. M.R.A. acknowledges the Royal Society for the provision of a Wolfson Merit Award. Assistance from Ka To Fung and Wong Yunn Shyuan with polymer sample preparation and characterization is kindly acknowledged. Assistance from Emily Smith with XPS measurements is kindly acknowledged.

Received: September 12, 2013

Revised: December 6, 2013

Published online: February 4, 2014

- [1] J. W. Costerton, P. S. Stewart, E. P. Greenberg, *Science* **1999**, *284*, 1318.
- [2] H. Y. Dang, C. R. Lovell, *Appl. Environ. Microbiol.* **2000**, *66*, 467.
- [3] J. A. Callow, M. E. Callow, *Nat. Commun.* **2011**, *2*, 244.
- [4] M. A. Cole, N. H. Voelcker, H. Thissen, H. J. Griesser, *Biomaterials* **2009**, *30*, 1827.
- [5] A. L. Hook, N. Voelcker, H. Thissen, *Acta Biomater.* **2009**, *5*, 2350.
- [6] C. D. L. Alarcon, B. Twaites, D. Cunliffe, J. R. Smith, C. Alexander, *Int. J. Pharm.* **2005**, *295*, 77.
- [7] D. Cunliffe, C. D. Alarcon, V. Peters, J. R. Smith, C. Alexander, *Langmuir* **2003**, *19*, 2888.
- [8] D. Cunliffe, C. A. Smart, J. Tsibouklis, S. Young, C. Alexander, E. N. Vulfson, *Biotechnol. Lett.* **2000**, *22*, 141.
- [9] G. Cheng, H. Xite, Z. Zhang, S. F. Chen, S. Y. Jiang, *Angew. Chem. Int. Ed.* **2008**, *47*, 8831.
- [10] J. Lee, J. Jung, K. Na, P. Heo, J. Hyun, *ACS Appl. Mater. Interfaces* **2009**, *1*, 1359.
- [11] A. L. Hook, D. J. Scurr, D. G. Anderson, R. Langer, P. Williams, M. Davies, M. R. Alexander, *Surf. Interface Anal.* **2013**, *45*, 181.
- [12] A. L. Hook, D. G. Anderson, R. Langer, P. Williams, M. C. Davies, M. R. Alexander, *Biomaterials* **2010**, *31*, 187.
- [13] D. L. Swerdlow, B. A. Woodruff, R. C. Brady, P. M. Griffin, S. Tippen, H. D. Donnell, E. Geldreich, B. J. Payne, A. Meyer, J. G. Wells, K. D. Greene, M. Bright, N. H. Bean, P. A. Blake, *Ann. Internal Med.* **1992**, *117*, 812.
- [14] A. I. Hidron, J. R. Edwards, J. Patel, T. C. Horan, D. M. Sievert, D. A. Pollock, S. K. Fridkin, *Infection Control Hospital Epidemiol.* **2008**, *29*, 996.
- [15] K. Schumm, T. B. Lam, *Cochrane Database Syst. Rev.* **2008**, *16*, CD004013.
- [16] A. L. Hook, C. Chang, J. Yang, J. Luckett, A. Cockrayne, S. Atkinson, Y. Mei, R. Bayston, D. J. Irvine, R. Langer, D. G. Anderson, P. Williams, M. C. Davies, M. R. Alexander, *Nat. Biotechnol.* **2012**, *30*, 868.
- [17] A. L. Hook, C. Chang, J. Yang, S. Atkinson, R. Langer, D. G. Anderson, M. C. Davies, P. Williams, M. R. Alexander, *Adv. Mater.* **2013**, *25*, 2542.

- [18] L. K. Ista, V. H. Perez-Luna, G. P. Lopez, *Appl. Environ. Microbiol.* **1999**, *65*, 1603.
- [19] C. A. White-Ziegler, S. Um, N. M. Prez, A. L. Berns, A. J. Malhowski, S. Young, *Microbiol. Sgm.* **2008**, *154*, 148.
- [20] D. McDougald, S. A. Rice, N. Barraud, P. D. Steinberg, S. Kjelleberg, *Nat. Rev. Microbiol.* **2012**, *10*, 39.
- [21] J. B. Kaplan, D. H. Fine, *Appl. Environ. Microbiol.* **2002**, *68*, 4943.
- [22] E. Wischerhoff, K. Uhlig, A. Lankenau, H. G. Borner, A. Laschewsky, C. Duschl, J. F. Lutz, *Angew. Chem. Int. Ed.* **2008**, *47*, 5666.
- [23] A. K. Epstein, T. S. Wong, R. A. Belisle, E. M. Boggs, J. Aizenberg, *Proc. Natl. Acad. Sci. U. S. A.* **2012**, *109*, 13182.
- [24] P. Kingshott, J. Wei, D. Bagge-Ravn, N. Gadegaard, L. Gram, *Langmuir* **2003**, *19*, 6912.
- [25] S. Balamurugan, S. Mendez, S. S. Balamurugan, M. J. O'Brien, G. P. Lopez, *Langmuir* **2003**, *19*, 2545.
- [26] A. Synytska, E. Svetushkina, N. Puretskiy, G. Stoychev, S. Berger, L. Ionov, C. Bellmann, K. J. Eichhorn, M. Stamm, *Soft Matter* **2010**, *6*, 5907.
- [27] M. Taylor, A. J. Urquhart, M. Zelzer, M. C. Davies, M. R. Alexander, *Langmuir* **2007**, *23*, 6875.